

## Advanced Materials

# Rhodeftal<sup>®</sup> 210\*

BINDER FOR THERMOSTABLE PAINTS / LUBRICANTS / ADHESIVES /  
 IMPREGNATION AND VARNISH

<b>DESCRIPTION</b>	Rhodeftal <sup>®</sup> 210 is a polyamide-imide (PAI). Appearance <span style="float: right;">brown liquid</span> Solids content (2 hours at 210 °C) <span style="float: right;">27-29 %</span> Viscosity at 25 °C <span style="float: right;">2500-4000 mPa·s</span> Solvent <span style="float: right;">N-Ethylpyrrolidone (NEP)</span>
<b>SPECIFIC PROPERTIES</b>	<ul style="list-style-type: none"> <li>• Heat class 220 °C-250 °C</li> <li>• Good dielectric rigidity and satisfying flexibility.</li> <li>• Good chemical properties</li> <li>• Outstanding adhesion at elevated temperature</li> <li>• Mixable with Epoxy Resin to reach very good flexibility</li> </ul>
<b>APPLICATIONS</b>	Rhodeftal <sup>®</sup> 210 may be used for the preparation of thermostable paints. These paints have good adhesion on the usual materials, and good resistance to heat, cold and weathering. Rhodeftal <sup>®</sup> 210 is particularly designed for the impregnation of coils for electrical devices and for wire enamel. Rhodeftal <sup>®</sup> 210 is used as a protection varnish or, associated with appropriate additives and fillers, it can be used as self-lubricating coatings or thermal insulation layers.
<b>STORAGE</b>	Rhodeftal <sup>®</sup> 210 may be stored at room temperature. It is storable for 2-3 years. Some increase of viscosity could be corrected by adding of solvent.

\* In addition to the brand name product denomination may show different appendices, which allows us to differentiate between our production sites: e.g. BD = Germany, US = United States, IN = India, CI = China, etc. These appendices are in use on packaging, transport and invoicing documents. Generally the same specifications apply for all versions. Please address any additional need for clarification to the appropriate Huntsman contact.

**USE IN PAINTS**
**Fillers, Pigments and Additives**

Fillers are chosen in order to increase or at least not to reduce the thermal stability of the coating and in addition to impart special properties to the paint.

Zinc powder may be used for primer coats in anti corrosion systems. Titanium dioxide such as Kronos RN 59, talc, barium sulfate, aluminium paste may be employed for finishing coats.

**Pigments** must have good heat stability.

**Solvents and diluents** are used to lower the viscosity. A number of products are suitable and behave either as solvents or as diluents.

Diluent	Maximum amount for 100 g Rhodetal 210
N-Ethylpyrrolidone (NEP)	>120 g
Dimethylformamide (DMF)	>120 g
Dimethylacetamide (DMAc)	>120 g
Dimethylsulfoxyde (DMSO)	>120 g
g-Butyrolactone (GBL)	>120 g
Benzonitrile	>120 g
Dioxane	<100 g
Methylglycolacetate	< 80 g
2-Nitropropane (2NP)	< 60 g
Ethylglycolacetate	< 60 g
Ethylacetate	< 60 g
Xylene	< 60 g
Toluene	< 65 g
Methylisobutylketone	< 30 g

The two following solvent systems provide good results with respect to paint processability and high gloss:

Dimethylformamide 1 part per weight

2-Nitopropane 1 part per weight

N-Ethylpyrrolidone 1 part per weight

Dimethylformamide 1 part per weight

Ethylglycolacetate 2 parts per weight

Of course a part from these two mixtures, other solvent systems can be used.

However products of low volatility such as NEP for example should not be used in too large amounts. It is not advisable to introduce a diluent such as xylene without premixing with a solvent such as DMF to avoid local precipitation of the polymer, which disappears under agitation. This phenomenon is due to temporary local excess of diluent. Chlorinated solvents must be avoided since they will cause the solution to gel. Anhydrous solvents or diluents should be used to obtain optimum results. The fact that NEP and DMF are hygroscopic solvents should be taken into account.

**USE IN PAINTS  
(CONTINUED)****Additives**

In case of application on vertical surfaces the addition of thixotropic agent will avoid dripping and sagging.

Aerosil 200 silica used at a level of 0.3 to 0.5% on Rhodofal<sup>®</sup> 210 is effective to impart good thixotropic properties. Beyond these concentrations it tends to give paints with reduced gloss. Silica must be ground with the other components. It is better, before introducing silica into the mix, to prepare a mixture of about 5 % silica in a nonpolar solvent such as xylene in a turbine mixer, which makes its dispersion into the paint easier.

Bentone 27 gives about the same results as Aerosil 200.

In order to prevent the formation of defects such as poor leveling and discoloration we advise using Nuosperse 657<sup>(1)</sup> at a level of 0.2 g per 100 g of Rhodofal<sup>®</sup> 210. In addition for very difficult coating conditions we advise adding BYK 310<sup>(2)</sup> at a level of 0.025 to 0.05 g per 100 g of Rhodofal<sup>®</sup> 210.

These additives must be preferably incorporated into the paint before grinding. They tend to settle on storage but simple stirring restores their dispersion in the paint medium.

<sup>(1)</sup> Rhône-Poulenc Chimie, 88 Boulevard Des Belges, F-69006 Lyon

<sup>(2)</sup> BYK-Chemie GmbH, Abelstrasse 14, D-4230 Wesel; FDA 175.300 approved

**Preparation of the paints**

The usual methods (three rolls or ball mill) can be employed. In the latter case homogenisation is achieved in about 72 hours. Generally all the paint components should be ground at the same time.

Depending on the gloss, heat resistance and physical properties various pigment/binder ratios can be used.

**Preparation of substrates**

The substrates must be very clean, carefully degreased (washing with trichloroethylene and rinsing with acetone) and dried. Non-metallic substrate (glass, asbestos...) are cleaned by exposure at 300 °C.

**Coating process**

Small pieces may be coated either by dipping, brushing or with a spray gun (with either hot or cold paint).

Large surfaces may be also coated with an airless gun using hot or cold paint. It is also possible to use an electrostatic gun.

In the case of a formula well adjusted from the point of view of solvent and thixotropy, the coating can be made on a cold substrate without dripping. A 15 µ dry film can then be applied without blistering. In case of a substrate of very intricate shape it may be advisable to preheat the piece at about 80-90°C.

Curing must be performed at 220 °C minimum but it is better carried out at 250 °C in order to obtain good end properties.

- 3 min. at 250 °C for very flexible paints
- 5 min. at 250 °C usual curing time
- 15 min. at 250 °C for very good chemical resistance

Curing at 300 °C for 2 to 5 min. also gives good results. The caloric capacity of the painted pieces must be taken into account. The above curing times are given for small pieces. Larger pieces need longer times or higher temperatures. When it is necessary to apply several coats of paint in order to obtain good adhesion it is better not to dry completely the preceding coat. 1 to 2 min. curing at 250 °C gives excellent results.

Curing of paints with Rhodofal 210 may also be made by IR irradiation. In this case, for a 6 W/cm<sup>2</sup> apparatus, we recommend 5 min. at about 5 cm from the coated substrate.

**USE IN PAINTS  
(CONTINUED)**
**Formulations**

The following formulations illustrate the main use of Rhodftal® 210. They must be considered as base formulations and should be adjusted to each particular case.

**Glossy paint of different colors**

Rhodftal® 210	100
Pigments inorganic	15
DMF	27.5
2NP	27.5
Dispersion of 5% Aerosil 200 in xylene	8
Nuosperse 657	0.2
BYK 310	0.025

**Glossy black paint**

Rhodftal® 210	100
Special black 4 Degussa	2.5
DMF	27
2NP	27
Nuosperse 657	0.2
BYK 310	0.025

**Industrial red iron oxide coat**

Rhodftal® 210	100
Red iron oxide 130 F	45
NEP/xylene 60/40	120
Nuosperse 657	0.3
BYK 310	0.025

This paint gives a mat finish.

**Aluminium paint (type car exhaust pipe)**

Rhodftal® 210	100
Aluminium paste	15
NEP/xylene 60/40	76
BYK 310	0.025

This paint has a thermal resistance of 1000 h at 300 °C.  
Chalking begins after about 200 hours.

All these paints have a good thermal stability. Light shades are however more sensitive because the resin may become discolored without significantly altering the mechanical and adhesion properties.

**We can say that for 1000 hours and more:**

- Light shades are stable at 200 °C
- Dark shades are stable at 220 °C
- Black and very dark shades are stable at 250 °C
- Non-hammer finished aluminium paints are stable at 300 °C

**Protective paints**

Besides their thermal stability these paints show good resistance to salt spray. This requires the application of an anti-corrosion primer followed by the application of a finishing coat.

Where temperatures do not exceed 300 °C we recommend the use on steel or aluminium substrates of zinc powder or strontium chromate in the formulation of the primer.

For the under coat we propose the following formulation:

Rhodftal® 210	100
Zinc powder	130
NEP/xylene 60/40	100
Aerosil 200	2
Nuosperse 657	0.1
Byk 310	0.05

The formulations for decorative coats quoted previously may be used as finishing coats. For good stability at 300 °C we recommend formulations including red iron oxide 130 °F, black special 4 or aluminium powder.

**HANDLING  
PRECAUTIONS**
**Personal hygiene**
*Safety precautions at workplace*

protective clothing	yes
gloves	essential
arm protectors	recommended when skin contact likely
<u>goggles/safety glasses</u>	<u>yes</u>

*Skin protection*

before starting work	Apply barrier cream to exposed skin
after washing	Apply barrier or nourishing cream

*Cleansing of contaminated skin*

Dab off with absorbent paper, wash with warm water and alkali-free soap, then dry with disposable towels. Do not use solvents

*Disposal of spillage*

Soak up with sawdust or cotton waste and deposit in plastic-lined bin

*Ventilation*

of workshop	Renew air 3 to 5 times an hour
of workplaces	Exhaust fans. Operatives should avoid inhaling vapours

**FIRST AID**

Contamination of the eyes by resin, hardener or mix should be treated immediately by flushing with clean, running water for 10 to 15 minutes. A doctor should then be consulted.

Material smeared or splashed on the skin should be dabbed off, and the contaminated area then washed and treated with a cleansing cream (see above). A doctor should be consulted in the event of severe irritation or burns. Contaminated clothing should be changed immediately.

Anyone taken ill after *inhaling* vapours should be moved out of doors immediately. In all cases of doubt call for medical assistance.

**IMPORTANT LEGAL NOTICE**

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT WITHOUT LIMITATION, AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Rhodeftal is a registered trademark of Huntsman Corporation or an affiliate thereof.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.



**service chimie**  
Emmanuel BAILLY  
Direction  
[E.Bailly@Service-Chimie.fr](mailto:E.Bailly@Service-Chimie.fr)

5, place de l'Église  
Saint Thibault des Vignes  
77400 Marne la Vallée  
France

Tél. : 33 (0)1 64 30 89 22  
Fax : 33 (0)1 64 30 87 49  
[Contact@Service-Chimie.fr](mailto:Contact@Service-Chimie.fr)  
[www.Service-Chimie.fr](http://www.Service-Chimie.fr)