



## Technical Data Sheet

# Fluorolink® MD700

## Perfluoropolyether

**Fluorolink® MD700** is a bifunctional PFPE-urethane methacrylate.

When used as the main component of a photocurable formulation, **Fluorolink® MD700** is suitable as an oligomer for producing low optical loss polymeric waveguides and cladding of optical fibres.

**Fluorolink® MD700** can also be used as a surface modifying additive in acrylic UV-curable systems: in fact, thanks to its tendency to migrate to the air-coating interface, **Fluorolink® MD700** imparts outstanding water/oil repellency and antifingerprint properties.

Property	Typical Value	Unit
Functional groups	Urethane methacrylate	
Dynamic viscosity at 20 °C	430	cP
Fluorine content	52	% w/w
Average molecular weight	~ 2,000	amu


## UV curing

When used as an additive at low dosage (0.1 – 0.5 % w/w) into a UV-curable formulation, **Fluorolink® MD700** does not require special curing conditions, while UV-curing under nitrogen is recommended whenever the **Fluorolink® MD700** is used as the major component of the photocurable formulation.

The recommended photo-initiators are based on  $\alpha$ -hydroxyketones and acyl-phosphineoxides, whose combination is synergic, at a 1-2 % w/w level.

## Solvent solubility

For solution processing of **Fluorolink® MD700**, figure 1 shows the product solubility in selected solvents. We recommend that solubility of each batch be checked upfront before starting any solution process.



## Shelf-life

Even if the product shows an excellent shelf-life, it is recommended to avoid long and direct exposure to strong light sources.



Progress beyond

[www.solvay.com](http://www.solvay.com)[SpecialtyPolymers.EMEA@solvay.com](mailto:SpecialtyPolymers.EMEA@solvay.com) | Europe, Middle East and Africa[SpecialtyPolymers.America@solvay.com](mailto:SpecialtyPolymers.America@solvay.com) | Americas[SpecialtyPolymers.Asia@solvay.com](mailto:SpecialtyPolymers.Asia@solvay.com) | Asia Pacific

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products. Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks are property of the companies that comprise Solvay Group or their respective owners.

© 2016 Solvay Specialty Polymers. All rights reserved. R 09/2020 | Version 1.1 Design by Peterman.it