



Galden®



SOLVAY

asking more from chemistry®

Galden® SV Fluids
CFC-free Solvents for Safer Operations

 **service chimie**

 5 place de l'Église
74400 Saint Thibault des Vignes
France

 +33 (0) 164 308 922
 +33 (0) 164 308 749
 hse@service-chimie.fr
 www.service-chimie.fr

**SPECIALTY
POLYMERS**

Features and Benefits

Galden® SV solvent fluids are low molecular weight Perfluoropolyethers (PFPEs) which exhibit a wide range of boiling points from 55 °C to 135 °C, and they are:

- Safe
- Non flammable
- Non toxic

Therefore, they can be used for cleaning operations where solvents are:

- Applied to hot components
- Heated prior to application
- Pressure sprayed onto components

Galden® SV fluids have Zero Ozone Depletion Potential (Zero ODP): they do not contain Chlorofluorocarbons (CFCs) chlorine, bromine and iodine. They do not require particular safeguard precautions or use-restrictions and they are fully compatible with all metals, a wide variety of rubbers and commercially available elastomers and plastics.

Galden® SV fluids are formulated to be compatible and fully miscible with PFPE oils and greases. They are fully miscible with Perfluorocarbon (PFC) fluids and with Chlorotrifluoroethylene (CTFE) oils above 45 °C.

Applications

Whether alone or in conjunction with other solvents, Galden® SV fluids perform well in many electronic and semiconductor cleaning functions, such as:

- Pump cleaning
- Degreasing
- Vapor blanketing
- Improving flash point
- Eliminating traces


They are the recommended solvent/carrier for the wide range of Solvay Specialty Polymers PFPE fluids and lubricant marketed under the Fomblin® trademark.

Typical Properties

(not for specification purpose)

Properties	Units	SV55	SV70	SV80	SV110	SV135
Boiling point	°C	55	70	80	110	135
Density	g/cm ³	1.65	1.68	1.68	1.71	1.72
Surface tension	Dyne/cm	14	14	16	16	17
Kinematic viscosity at 25 °C	cSt	0.45	0.50	0.57	0.77	1.00
Heat of vaporization at boiling point	cal/g	22	17	17	16	16
Vapor pressure at 20 °C	torr	228	141	62	17	8
Solubility of water	ppm	<10	<10	<10	<10	<10
Flash point	°C	None	None	None	None	None
Fire point	°C	None	None	None	None	None
Autoignition temperature	°C	None	None	None	None	None
ODP	-	0	0	0	0	0

Vapor pressure vs. temperature



www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia Pacific



SOLVAY

asking more from chemistry®

Impression du 09/05/2022

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products. Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks are property of the companies that comprise Solvay Group or their respective owners.

© 2015 Solvay Specialty Polymers. All rights reserved. R 12/2015 | Version 2.1 Brochure design by ahlersheinel.com

Service Chimie